

**Table 3. Number of condom-use experiences reported, by type of condom**

Experience	Polyurethane	Latex
<b>Total uses attempted</b>	<b>1,036</b>	<b>1,023</b>
Not used for intercourse	11	22
Defective	0	1
Could not put on/unroll	8	6
Did not fit	2	12
Broke while putting on	1	3
<b>Used for intercourse</b>	<b>1,025</b>	<b>1,001</b>
Did not complete intercourse	88	15
Broke	74	11
Slipped off	14	4
<b>Completed intercourse</b>	<b>937</b>	<b>986</b>
Slipped off during withdrawal	23	2
<b>Successfully used</b>	<b>914</b>	<b>984</b>

*Note:* Table is based only on the number of condoms for which use was attempted.