Table 3. Number of condom-use experiences recorded in the first five uses per couple, by type of condom

Experience	Polyure-thane	Latex
Total uses attempted	**1,823**	**1,894**
Nonclinical failures	19	12
Could not put on/unroll	16	5
Broke while putting on	0	4
Did not fit	1	1
Insufficient lubrication	2	1
Defective	0	1
Used for intercourse	**1,804**	**1,882**
Clinical failures	154	31
Broke during intercourse	66	7
Broke on withdrawal	6	1
Slipped off during intercourse	22	3
Slipped off on withdrawal	60	20
Completed intercourse	**1,650**	**1,851**
Broke during removal	6	0
Successfully used	**1,644**	**1,851**